

AD-A284 859

MENTATION PAGE

Dist: A

Form Approved
OMB No. 0704-0186

Estimated to average 1 hour per response, including the time for review of the report, preparation of the response, and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this burden to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0186), Washington, DC 20503.

REPORT DATE

3. REPORT TYPE AND DATES COVERED

ANNUAL 01 Aug 93 TO 31 Jul 94

4. TITLE AND SUBTITLE

AASERT-93 ELECTROPLATING OF REFRACTORY METALS USING
HALOALUMINATE MELTS

5. FUNDING NUMBERS

F49620-93-1-0463

61103D

3484/XS

6. AUTHOR(S)

Prof Gleb Mamantov

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

Dept of Chemistry
Univ of Tennessee
575 Buehler Hall
Knoxville, TN 37996-16008. PERFORMING ORGANIZATION
REPORT NUMBER

AEOSR-TR- 94 0580

9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)

AFOSR/NL
110 DUNCAN AVE SUITE B115
BOLLING AFB DC 20332-0001
Maj Erstfeld10. SPONSORING / MONITORING
AGENCY REPORT NUMBER

11. SUPPLEMENTARY NOTES

94-30473

12a. DISTRIBUTION / AVAILABILITY STATEMENT

Approved for public release;
distribution unlimited

SPX

V CODE

A

13. ABSTRACT (Maximum 200 words)

The main objective of this research, performed by Sven E. Eklund, a graduate student at the Univ of Tennessee, Knoxville, is to explore the fundamentals of electroplating of several refractory metals, such as tungsten and tantalum, from chlorofluoroaluminate melts and to compare with electroplating of these elements from the LiF-NaF-KF eutectic. There has been considerable interest in the electrochemistry and metallurgy of the Groups IV-B, V-B, and VI-B transition metals (so-called refractory metals) because of the potential use of these metals in electronic components, electrical devices, and the aerospace industry. Pure, coherent deposits of these metals were originally obtained by a method developed by Mellors and Senderoff [1] in 1965. This method uses electrolytic reduction to the metal from the ternary eutectic LiF-NaF-KF, or FLINAK. Mechanisms proposed in several articles by Senderoff and coworkers for the reduction of several metals [2-5] have spurred research into the refractory metals in molten fluorides.

(DTIC QUALITY INSPECTED 3)

14. SUBJECT TERMS

15. NUMBER OF PAGES

16. PRICE CODE

17. SECURITY CLASSIFICATION
OF REPORT

(U)

18. SECURITY CLASSIFICATION
OF THIS PAGE

(U)

19. SECURITY CLASSIFICATION
OF ABSTRACT

(U)

20. LIMITATION OF ABSTRACT

(U)

First Annual Technical Report

AF Grant F49620-93-1-0463

Electroplating of Refractory Metals Using Haloaluminate Melts.

August 31, 1994

Gleb Mamantov
Principal Investigator

DTIC QUALITY INSPECTED 3

The main objective of this research, performed by Sven E. Eklund, a graduate student at the University of Tennessee, Knoxville, is to explore the fundamentals of electroplating of several refractory metals, such as tungsten and tantalum, from chlorofluoroaluminate melts and to compare with electroplating of these elements from the LiF-NaF-KF eutectic.

There has been considerable interest in the electrochemistry and metallurgy of the Groups IV-B, V-B, and VI-B transition metals (so-called refractory metals) because of the potential use of these metals in electronic components, electrical devices, and the aerospace industry. Pure, coherent deposits of these metals were originally obtained by a method developed by Mellors and Senderoff[1] in 1965. This method uses electrolytic reduction to the metal from the ternary eutectic LiF-NaF-KF, or FLINAK. Mechanisms proposed in several articles by Senderoff and coworkers for the reduction of several metals [2-5] have spurred research into the refractory metals in molten fluorides.

Most of our studies of refractory metals have been performed in alkali chloroaluminates. By comparison with FLINAK, sodium chloroaluminate ($\text{AlCl}_3\text{-NaCl}$) melts may be considered as favorable systems in several respects. First, the liquidus temperatures for chloroaluminates lie below 200°C for melt compositions in the range from 49.8 to 100 mole percent AlCl_3 , while FLINAK has a eutectic point of 454°C , and generally temperatures in excess of 750°C are required for refractory metal deposition. The Lewis melt acidity can be varied over a broad range by changing the AlCl_3 to NaCl ratio. Finally, the highly aggressive nature of fluoride melts and the temperatures required for their use greatly limit the materials which can be used for bath construction, whereas chloroaluminate studies can be conducted using even simple Pyrex cells.

Studies of the reduction of tantalum (V) [6], niobium (V) [7], and tungsten (VI) [8], in acidic (AlCl_3 -rich) alkali chloroaluminates show that low oxidation state cluster species, such as $\text{Ta}_6\text{Cl}_{14}$ and W_6Cl_{12} , are formed which, due to high stability and/or insolubility in the melt, prevent further reduction to the metal. In basic (usually $\text{AlCl}_3\text{-NaCl}_{\text{sat}}$) melts, problems can arise because of small amounts of oxide-containing species. This contamination by oxides, arising either from atmospheric impurities or attack of Pyrex by the melt, can be greatly reduced by passing phosgene or carbon tetrachloride through the melt [9,10].

Fluoride-containing chloroaluminate melts are a possible compromise between the use of fluoride melts, which require somewhat severe conditions, and low-temperature chloroaluminate melts. It was felt initially that the inclusion of fluoride into the chloroaluminate melts may sufficiently inhibit the formation of cluster species as to allow reduction to the metal.

Recently we have extended our studies of selected refractory metals, specifically niobium, tantalum and tungsten, to basic AlCl_3 - NaCl which has been treated with COCl_2 to remove oxide impurities. The electrochemistry of these elements is being studied as a function of temperature. Also, the electrochemistry in basic chloroaluminates is being compared with that observed in sodium fluorochloroaluminates or NAFCAL. We have determined that all three elements can be deposited from either basic NaAlCl_4 or NAFCAL at temperatures lower than those required for deposition from FLINAK (600 to 650°C compared to 750°C for FLINAK). Further studies are needed to determine the quality of the deposit (or plate). We have also conducted plating of Ta and Nb from FLINAK; the plates appear to be comparable to those reported by Senderoff and Mellors[5] although significant electrochemical differences with those of Senderoff and Mellors were observed.

The reduction of Ta(V) in AlCl_3 - NaCl_{sat} melts containing 10 mole % NaF was investigated by voltammetric and spectroscopic methods, and exhaustive electrolysis at 200-450°C (11). The reduction to Ta metal proceeds through the formation of Ta(IV), Ta(III), and Ta(II). The species involving Ta(III) and Ta(II) are very unstable forming clusters $\text{Ta}_6\text{Cl}_{12}^{3+}$ and $\text{Ta}_6\text{Cl}_{12}^{2+}$ which are slowly reduced to metallic tantalum.

The reduction of Nb(V) in AlCl_3 - NaCl_{sat} melts at 180°C also involves the formation of Nb(IV) and cluster species Nb_3^{3+} and Nb_6^{15+} ; temperatures >525°C were needed for the deposition of Nb metal (12). Additions of NaF had little, if any, effect on the nature of the deposit formed.

The reduction of W(V) in AlCl_3 - NaCl_{sat} was studied to determine the effect of oxide (13); these studies are continuing.

The current studies utilize a vacuum tight quartz cell which contains a glassy carbon crucible containing the melt. Initial experiments have been conducted with FLINAK as the solvent; the components of FLINAK (LiF , NaF , KF) were recrystallized to minimize oxide content (14).

Initially, the cyclic voltammetry of Ta(V) (added as K_2TaF_7) in FLINAK was briefly explored; three reduction waves were observed. Currently we are examining the electrochemical behavior of tungsten in FLINAK. The compound WF_4 was synthesized to be used as the solute; however, it was learned that WF_4 decomposes above 300°C. We are now adding gaseous WF_6 to FLINAK containing metallic tungsten; according to Mellors and Senderoff(15) this approach results in an intermediate oxidation state of tungsten which we plan to characterize by spectroscopic methods.

REFERENCES

1. G. W. Mellors and S. Senderoff, *J. Electrochem. Soc.*, 112, 266 (1965).
2. S. Senderoff, G. W. Mellors, and W. J. Reinhart, *ibid.*, 112, 840 (1965).
3. G. W. Mellors and S. Senderoff, *ibid.*, 113, 60 (1966).
4. G. W. Mellors and S. Senderoff, *ibid.*, 113, 66 (1966).
5. S. Senderoff and G. W. Mellors, *Science*, 153, 1475 (1966).
6. J. H. von Barner, L. E. McCurry, C. A. Jorgensen, N. J. Bjerrum, and G. Mamantov, *Inorg. Chem.*, 31, 1034 (1992).
7. G. Ting, K. W. Fung, and G. Mamantov, *J. Electrochem. Soc.*, 123, 624 (1976).
8. J.-P. Schoebrechts, P. A. Flowers, G. W. Hance, and G. Mamantov, *J. Electrochem. Soc.*, 135, 3057 (1988).
9. I-Wen Sun, K. D. Sienerth, and G. Mamantov, *J. Electrochem. Soc.*, 138, 2850 (1991).
10. G.-S. Chen, I.-W. Sun, K. D. Sienerth, A. G. Edwards, and G. Mamantov, *J. Electrochem. Soc.*, 140, 1523 (1993).
11. G.-S. Chen, A. G. Edwards, and G. Mamantov, *J. Electrochem. Soc.*, 140, 2439 (1993).
12. K. D. Sienerth, E. M. Hondrogiannis, and G. Mamantov, *J. Electrochem. Soc.*, 141, 1762 (1994).
13. I.-W. Sun, A. G. Edwards, and G. Mamantov, *J. Electrochem. Soc.*, 140, 2733 (1993).
14. K. D. Sienerth, Ph.D. Dissertation, University of Tennessee, 1992.
15. S. Senderoff and G. W. Mellors, *J. Electrochem. Soc.*, 114, 586 (1967).

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution	
Availability Codes	
Dist	Avail and/or Special
A-1	